

THREADED ROD
CLASS 8.8 METRIC



APPLICATION


Bremick® Threaded Rod Metric Class 8.8 is designed for industrial and construction applications where high tensile superior performance is required



PRODUCT ATTRIBUTES

Material Class:	Carbon Steel Class 8.8
Thread Form:	Metric 6g
Finish:	Plain/Black/Natural
Standard:	Complies to DIN 976-1:2016
Mechanical Properties:	Complies to ISO 898.1:2013
Chemical Composition:	Complies to ISO 898.1:2013

MARKING



MECHANICAL PROPERTIES

PROPERTIES	TENSILE STRENGTH (MPa)	STRESS UNDER PROOF LOAD (MPa)	HARDNESS					
	MIN	NOM.	VICKERS (HV)		BRINELL (HBW)		ROCKWELL (HRC)	
CLASS 8.8 ≤ M16	800	580	250	320	245	316	22	32
CLASS 8.8 >M16	830	600	255	335	250	331	23	34


CHEMICAL COMPOSITION (%)

MATERIAL	C		P	S	B	TEMPERING TEMPERATURE °C
	MIN	MAX	MAX	MAX	MAX	MIN
CARBON STEEL	0.25	0.55	0.025	0.025	0.003	425

FINISH INFORMATION

PLAIN / BLACK / NATURAL		
DESCRIPTION	OVERVIEW	CORROSION RESISTANCE
Plain, Black & Natural are all terms referring to the fastener not having a coating applied. The product has a light oil added.	Plain or uncoated fasteners offer no corrosion protection they are supplied lightly oiled to inhibit the rust process prior to installation and help during installation.	—

DIMENSIONAL DATA (mm)



DIAMETER (mm)	PITCH	MAJOR DIAMETER (d1)	
		MIN	MAX
M5	0.80	4.826	4.976
M6	1.00	5.794	5.974
M8	1.25	7.760	7.927
M10	1.50	9.732	9.968
M12	1.75	11.701	11.966
M14	2.00	13.682	13.962
M16	2.00	15.682	15.962
M20	2.50	19.632	19.958
M24	3.00	23.577	23.952
M27	3.00	26.577	26.952
M30	3.50	29.522	29.947
M33	3.50	32.522	32.947
M36	4.00	35.465	35.940
M42	4.50	41.437	41.937
M48	5.00	47.399	47.929

LENGTH (mm)

NOMINAL	1000 (1m)	2440 (2.44m)	2570 (2.57m)	2700 (2.7m)	3000 (3m)	3600 (3.6m)
MIN	995.5	2432.5	2562.5	2692.5	2989.5	3589.5
MAX	1004.5	2447.5	2577.5	2707.5	3010.5	3610.5

Whilst every care was taken in the preparation of this publication, Bremick® accepts no responsibility for the accuracy of the information supplied. Bremick® reserves the right to make alterations to specifications as part of ongoing development and improvement. This publication serves as a guide and it's the responsibility of the end user to ensure suitability for their application.
The contents of this publication are the exclusive copyright of Bremick® and may not be reproduced without permission.

Bremick Pty Ltd
Head Office | 88 Dalmeny Avenue, Rosebery 2018
National Distribution Centre | M5/M7 Logistics Park,
Warehouse 4B, 290 Kurrajong Road, Prestons NSW 2170
www.bremick.com.au