


NYLON INSERT LOCK NUT
UNC F594H
STAINLESS STEEL



APPLICATION

Bremick® nylon insert nuts are used in a wide range of applications to reduce loosening due to vibration and other factors. The nylon thread is cut upon application and produced friction. Not recommended for repeat use

PRODUCT ATTRIBUTES

Material Class: 316 STAINLESS STEEL 2-CW2-F594H


Thread Form: Class 2B

Standard: Complies to ASME B18.16.6:2017

Mechanical Properties: Complies to ASTM F594:2024

Chemical Composition: Complies to ASTM F594:2024

MARKING



In some cases, the Bremick marking will be replaced by the mark of the original manufacturer

MECHANICAL PROPERTIES

ALLOY MECHANICAL PROPERTY MARKING	STRESS UNDER PROOF LOAD (ksi)	HARDNESS
		ROCKWELL
	MIN	RANGE
F594H	85	B80-C35


CHEMICAL COMPOSITION (%)

STAINLESS STEEL GRADE	C	Mn	P	S	Si	Ni	Cr	Mo
	MAX	MAX	MAX	MAX	MAX	RANGE	RANGE	RANGE
316	0.08	2.00	0.045	0.030	1.00	10.0-14.0	16.0-18.0	2.00-3.00

MATERIAL INFORMATION

STAINLESS STEEL 316		
DESCRIPTION	OVERVIEW	CORROSION RESISTANCE
316 is a Marine Grade SS – It contains 2-3% Molybdenum which provides highest possible corrosion protection than 304 Stainless steel.	Bremick® 316 Stainless Steel provides the ultimate level of protection and is recommended for external application and marine environments.	Ultimate

DIMENSIONAL DATA (inches)



DIAMETER (inches)	ACROSS FLATS (s)		ACROSS CORNERS (e)	TOTAL HEIGHT (h)		NUT HEIGHT (m)
	MIN	MAX		MIN	MAX	
3/4	1.052	1.064	1.191	0.860	0.890	0.742
7/8	1.239	1.252	1.403	0.969	0.999	0.790
1	1.427	1.440	1.615	1.016	1.078	0.825
1 1/8	1.614	1.627	1.826	1.141	1.203	0.930
1 1/4	1.801	1.815	2.038	1.360	1.422	1.125
1 3/8	1.973	2.008	2.232	1.547	1.609	1.282
1 1/2	2.159	2.197	2.444	1.578	1.640	1.313

SOCKET OR SPANNER SIZE (inches)

BOLT DIAMETER	3/4	7/8	1	1 1/8	1 1/4	1 3/8	1 1/2
SPANNER SIZE	1 1/8	1-5/16	1-1/2	1-11/16	1-7/8	2-1/6	2-1/4

Whilst every care was taken in the preparation of this publication, Bremick® accepts no responsibility for the accuracy of the information supplied. Bremick® reserves the right to make alterations to specifications as part of ongoing development and improvement. This publication serves as a guide and it's the responsibility of the end user to ensure suitability for their application.
The contents of this publication are the exclusive copyright of Bremick® and may not be reproduced without permission.

Bremick Pty Ltd
Head Office | 88 Dalmeny Avenue, Rosebery 2018
National Distribution Centre | M5/M7 Logistics Park,
Warehouse 4B, 290 Kurrajong Road, Prestons NSW 2170
www.bremick.com.au