

THREADED ROD UNC F593H
STAINLESS STEEL



STAINLESS
STEEL
316

APPLICATION

Bremick® Threaded Rod UNC 316 Stainless Steel is designed for industrial and construction applications where ultimate corrosion performance is required

PRODUCT ATTRIBUTES

Material Class: 316 STAINLESS STEEL 2-CW2-F593H

Thread Form: Class 2A

Standard: Complies to IFI-136:2002


Mechanical Properties: Complies to ASTM F593:2024

Chemical Composition: Complies to ASTM F593:2024

MARKING

End View

Colour Code: Pink



MECHANICAL PROPERTIES (Full-Size Tests)

ALLOY MECHANICAL PROPERTY MARKING	Tensile Strength (ksi)	Yield Strength (ksi)	HARDNESS
			ROCKWELL
	RANGE	MIN	RANGE
F593H	85~140	45	B80-C32


CHEMICAL COMPOSITION (%)

STAINLESS STEEL GRADE	C	Mn	P	S	Si	Cr	Ni	Mo
	MAX	MAX	MAX	MAX	MAX	RANGE	RANGE	RANGE
316	0.08	2.00	0.045	0.030	1.00	16.0-18.0	10.0-14.0	2.00-3.00

MATERIAL INFORMATION

STAINLESS STEEL 316		
DESCRIPTION	OVERVIEW	CORROSION RESISTANCE
316 is a Marine Grade SS – It contains 2-3% Molybdenum which provides highest possible corrosion protection than 304 Stainless steel.	Bremick® 316 Stainless Steel provides the ultimate level of protection and is recommended for external application and marine environments.	Ultimate

DIMENSIONAL DATA (inches)



DIAMETER (inches)	TPI	MAJOR DIAMETER (d1)	
	UNC	MIN	MAX
3/4	10	0.7353	0.7482
7/8	9	0.8592	0.8731
1	8	0.9830	0.9980
1 1/8	7	1.1064	1.1228
1 1/4	7	1.2314	1.2478
1 1/2	6	1.4794	1.4976

LENGTH (inches)

DIAMETER (Inches)	NOM.	3/4	7/8	1	1 1/8	1 1/4	1 1/2
36 (3 ft)	MIN	35.88	35.81				35.75
	MAX	36.12	36.19				36.25
144 (12 ft)	MIN	143.88	143.81				143.75
	MAX	144.12	144.19				144.25

Whilst every care was taken in the preparation of this publication, Bremick® accepts no responsibility for the accuracy of the information supplied. Bremick® reserves the right to make alterations to specifications as part of ongoing development and improvement. This publication serves as a guide and it's the responsibility of the end user to ensure suitability for their application.
The contents of this publication are the exclusive copyright of Bremick® and may not be reproduced without permission.

Bremick Pty Ltd
Head Office | 88 Dalmeny Avenue, Rosebery 2018
National Distribution Centre | M5/M7 Logistics Park,
Warehouse 4B, 290 Kurrajong Road, Prestons NSW 2170
www.bremick.com.au