

CARBON STEEL

UNC/UNF HEX NUTS

NUT GRADE	CHEMICAL COMPOSITION (%)			
	C	Mn	P	S
	MAX	MIN	MAX	MAX
2	0.55	-	0.12	0.15
5	0.55	0.30	0.05	0.15
8	0.55	0.30	0.04	0.05

Reference SAE 995 2017

Whilst every care was taken in the preparation of this publication, Bremick® accepts no responsibility for the accuracy of the information supplied. Bremick® reserves the right to make alterations to specifications as part of ongoing development and improvement. This publication serves as a guide and it's the responsibility of the end user to ensure suitability for their application.
The contents of this publication are the exclusive copyright of Bremick® and may not be reproduced without permission.

Bremick Pty Ltd
Head Office | 88 Dalmeny Avenue, Rosebery 2018
National Distribution Centre | M5/M7 Logistics Park,
Warehouse 4B, 290 Kurrajong Road, Prestons NSW 2170
www.bremick.com.au